



WW-HR SERIES

LINERLESS RUBBER SPLICING TAPE - 69kV

DESCRIPTION	FEATURES
<p>WW-HR is an ethylene rubber based high voltage tape with excellent electrical, chemical and physical properties. WW-HR is a linerless, self-bonding tape that permits much quicker taping speeds than a tape with a liner and yields a uniform, void-free build-up. The excellent stretch of WW-HR allows conformability to the most complex shapes and contour. WW-HR is compatible with all extruded cable insulations and is specially formulated to have excellent thermal conductivity that will allow the heat to dissipate from a joint. It is flame retardant and meets typical industry standards.</p>	<ul style="list-style-type: none"> Linerless Self-bonding Outstanding corona and ozone resistance High thermal conductivity and flame retardant Excellent moisture, corrosion, UV and chemical resistance Rated up to 69kV Lead free

MATERIALS	BACKING	ADHESIVE	COLOR	STANDARD SIZES (WIDTH X LENGTH)	PART NUMBER
	EPR rubber	Acrylic adhesive	Black	.75" x 30' (19mm x 9.1m) 1" x 30' (25mm x 9.1m) 1.5" x 30' (38mm x 9.1m) 2" x 30' (51mm x 9.1m)	WW-HR-75 WW-HR-10 WW-HR-15 WW-HR-20

TECHNICAL PROPERTIES	CHARACTERISTIC	TYPICAL VALUE	TEST METHOD
	Thickness (mils)	29.9	ASTM D 4325
	Breaking strength (psi)	333.6	ASTM D 412
	Elongation at break (%)	890	ASTM D 412
	Fusion (78.74 mils max.)	No flag	ASTM D 4325
	Heat resistance	266°F, 130°C	ASTM D 4325
	Operating temp.: Continuous	194°F, 90°C	ASTM D 4325
	Operating temp.: Emergency overload	266°F, 130°C	ASTM D 4325
	Water absorption (%)	0.06	ASTM D 570
	Ozone resistance	Pass	ASTM D 4325
	UV resistance	Pass	ASTM D 4325
	Dielectric strength (V/mil)	990.6	ASTM D 149
	Dissipation factor after water immersion	0.005	ASTM D 150
	Dissipation factor after hot water immersion	0.015	ASTM D 150
	Dielectric constant: after water immersion	2.9	ASTM D 150
	Dielectric constant: after hot water immersion	3.1	ASTM D 150
Volume resistivity (Ω.cm) 96h @ 23°C and 50% RH	1x10 ¹⁶	ASTM D 257	
Volume resistivity (Ω.cm) 96h @ 23°C and 96% RH	1x10 ¹³	ASTM D 257	

RECOMMENDED USES	STORAGE	SHELF LIFE
For insulating and jacketing of splices on power cable from 600 volts through 69,000 volts and for building stress cones and jacketing of terminations on power cable from 600 volts through 35,000 volts. Insulate and protect bus bars and joints.	In original packaging, placed in horizontal position under cover and temperature between 5°C and 35°C.	60 months from date of manufacture.

Data in table represents average test results and are not to be used for specification purpose. The product users should make their own tests to determine the products' suitability for the intended use

LIMITED WARRANTY: NSi Industries LLC warrants that each of its products will be free from material and manufacture defects at the date of shipment (unless specified otherwise). NSi Industries LLC makes or gives no warranty to the distributor, its customers, or the product's end user regarding the product's merchantability and/or suitability for their/its intended use or purpose, and buyer shall assume all risks associated therewith. Provided that the product is proven to be defective, NSi Industries sole obligation and buyer's exclusive remedy shall be through the distributor, at NSi Industries' discretion, to replace, repair, or refund the product proved to be defective within the time period specified above. EXCEPT AS EXPRESSLY SET FORTH HEREIN, NSI INDUSTRIES MAKES OR GIVES NO OTHER WARRANTIES, EXPRESSED OR IMPLIED. Except where prohibited by law, NSi Industries LLC will not be liable for collateral, consequential, indirect or incidental damages arising out of, or connected in any way with the supply of products.